



## AMBERJET™ UP6040

Semiconductor Grade Final Polishing Mixed Bed Resin

### Introduction

AMBERJET UP6040 resin is a semiconductor grade ion exchange resin mixed bed which is specifically designed and manufactured for final polishing service in the highest purity water treatment applications. This pre-mixed resin product is composed of an equivalent mixture of high capacity, fully regenerated strong acid and strong base gel type ion exchange resins. The resin mixture exhibits no clumping. The particle size of the component resins is specially designed to reduce the natural tendency of cation and anion resins to separate when handled in a water slurry. This ensures perfect mixed bed equilibrium performance, since the resins will remain intimately mixed in the final polishing vessels. The uniform particle size of the resins maximizes the kinetic performance of the mixed bed allowing the use of high service flow rates to achieve the ultimate balance of pressure drop and purity. All these characteristics are essential to produce water of the highest achievable purity with a minimum volume of rinse water.

AMBERJET UP6040 resin is specifically designed for use in non-regenerable final polishing mixed beds in ultrapure water systems in the semiconductor industry and similar demanding applications. The leakage of all ionic species, silica, total organic carbon, and sub-micron particles have all been driven to a new low level with Amberjet UP6040 resin. Free of the limitations imposed by regenerable systems, the characteristics of this semiconductor grade mixed bed resin concentrate on optimum properties during service. Amberjet UP6040 resin is not recommended for use in regenerable mixed bed applications.

### Basic resin properties

In non-regenerable final polishing applications, UPW performance is much more significant than basic resin properties. It is still important to know that the resins used in this application are of the highest capacity and total quality. The typical properties of the resin used in AMBERJET UP6040 resin are shown below. These values are listed to show that both the cation and anion resins used to make the AMBERJET UP6040 resin meet stringent standards for high capacity, uniform particle size ion exchange resins.

### Properties

	Cation H <sup>+</sup>	Anion OH <sup>-</sup>
Total exchange capacity, eq/L	≥ 2.00	≥ 1.10
Moisture holding capacity, %	44.0 - 51.0	54.0 - 60.0
Particle Size		
Uniformity coefficient	≤ 1.20	≤ 1.20
Harmonic mean size	0.60 - 70 mm	0.58 - 0.68 mm
H form                    % of sites	≥ 99	-
OH form                    % of sites	-	≥ 95.0
Cl form,                    % of sites	-	≤ 0.5
CO <sub>3</sub> form                    % of sites	-	≤ 5.0
SO <sub>4</sub> form                    % of sites	-	≤ 0.1

## Suggested Operating Conditions

Water Treatment	
Feed water temperature	15 to 25°C (60 to 77° F)
Minimum bed depth	900 mm (3 feet)
Service flow rate	30 to 50 BV*/h
Recommended <i>influent</i> water quality	
Inlet Resistivity	> 17 MΩ·cm
Inlet Silica	< 2 ppb
Inlet Total Organic Carbon	< 15 ppb


\* 1 BV (Bed Volume) = 1 m3 solution per m3 resin (1BV/h = 0.125 gpm/ft3)

## Quality assurance

AMBERJET UP6040 resin is tested by Dow Water & Process Solutions for resistivity, TOC, and kinetic performance. This insures that all batches of AMBERJET UP6040 resin will meet stringent UPW performance requirements on these most critical parameters.

Dow Water & Process Solutions will fully support the quality and performance of AMBERJET UP6040 resin in UPW applications in order to assure full customer satisfaction with the product as delivered.

Typical TOC and resistivity curves based on our quality control procedure for AMBERJET UP6040 resin are shown below.



### For more information about DOW™ resins, call the Dow Water & Process Solutions business:

North America: 1-800-447-4369  
 Latin America: (+55) 11-5188-9222  
 Europe: +800-3-694-6367  
 Italy: +800-783-825  
 South Africa: +0800 99 5078  
 Pacific: +8007776 7776  
 China: +400 889-0789  
<http://www.dowwaterandprocess.com>

Notice: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

