

Elastomer Compatibility Characteristics

UCON™ Oil-Soluble Polyalkylene Glycol (PAG) Lubricant Technology

What You Need to Know

- Elastomer compatibility is a key consideration when formulating lubricants
- UCON™ Oil-Soluble PAGs (OSPs) perform extremely well with HNBR and FKM elastomers
- Due to the complexity of elastomers, it is important to contact a Dow representative in order to learn how to best match OSP with a desired elastomer

Introduction

Oil-Soluble Polyalkylene Glycols (OSPs) can be used as a primary base oil, a co-base oil, or even a performance enhancing additive in formulations. To demonstrate OSP use in formulations, the compatibility of OSPs has been examined on common elastomers, with the following data.



Types of Elastomers

1. Nitrile Butadiene Rubber (NBR): co-polymer of polybutadiene and acrylonitrile; also called Buna N rubbers
2. Hydrogenated Nitrile Butadiene Rubbers (HNBR)
3. Fluoro-Elastomers (FKM): trade names include Viton, Tecnoflon, Fluorel and Aflas
4. Ethylene-Propylene Diene Monomer (EPDM) rubber: ethylene-propylene diene rubber, a terpolymer of ethylene, propylene and a diene component

UCON™ Oil-Soluble Polyalkylene Glycol (PAG) Lubricant Technology

Test Method

Each of these elastomers were evaluated for their compatibility using ISO-6072. This procedure is a static elastomer test in which the elastomer is submerged in the fluid for a period of 1000 hours. For NBR, HNBR and EPDM, the fluid temperature was maintained at 100°C, but for FKM, the temperature was 130°C.

Results

Base Oil	NBR	HNBR	FKM	EPDM
OSP-18	3	1	1	3
OSP-32	3	1	1	3
OSP-46	1	1	1	3
OSP-68	1	1	1	3
OSP-150	2	1	1	3
OSP-220	2	1	1	3
OSP-320	2	1	1	3
OSP-460	2	1	1	3
OSP-680	2	1	1	3

1 = Very Compatible

2 = Moderate Compatibility; it is recommended the specific manufacturer's grade is tested.

3 = Not Compatible

Note: It is always a good practice to examine the compatibility of your formulated lubricant with the type of elastomer used in the manufacturer's equipment since different compounding techniques for the same elastomer type can show some significant differences.

Explanation

NBR: Showed a broad range of compatibilities depending on the polymer molecular weight. While the lower molecular weight OSP grades showed moderate swelling, for OSP-150 and higher grades, elastomer shrinkage increased with increasing grade number. Therefore, it is sometimes recommended that OSP-18 or OSP-32 be added to higher viscosity OSP grades to negate NBR shrinkage. OSP-68 showed negligible volume change. Hardness number also showed a clear correlation to polymer molecular weight. The lower molecular weight OSP grades showed the highest level of softening whereas OSP-320 and 680 had a higher degree of hardening. Care should be taken in the selection of the optimum OSP grade when working with NBR.

HNBR: Showed excellent compatibility for all grades and is a preferred choice over NBR.

FKM: Showed excellent compatibility with OSP-18 through OSP-460 with about 1% volume change and minor softening. OSP-680 showed moderate volume shrinkage and minor softening.

EPDM: Showed significant volume shrinkage and hardening with all OSP grades and is not a good choice of elastomer with OSPs when the OSP is being used as the primary base oil in the lubricant composition.

Now You Know

Dow UCON™ OSPs deliver extended fluid life and improved equipment performance. To learn how you can benefit from OSPs or to get more out of your lubricant, contact our Customer Information Group (numbers below) or visit www.dow.com/ucon/osp to download a technical data sheet and request a sample.

Product Stewardship

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

North America:

Toll-free 1-800-447-4369

Europe:

Toll-free +800 3 694 6367
Call +31 11567 2626

Pacific:

Toll-free +800 7776 7776
Call +60 3 7965 5392

Latin America:

Call +55 11 5188 9000

©™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

www.dow.com/ucon/osp

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.